



0322.1517 High performance module

M460-HC144-w BF GG U40

Bifacial glass-glass module / White /
Mono HiR Half-cut / 40 mm U-frame



HiR half-cut technology



Additional yields through enhanced bifaciality factor



High performance stability and maximum efficiency



Meets highest aesthetic requirements



Very high durability due to glass-glass technology



Full traceability of all raw materials



Swiss development and warranty

Bifacial gain

Low reflecting surface	<i>e.g. grass, brick</i>	5 - 15 %
Well reflecting surface	<i>e.g. sand, bright gravel or paint</i>	15 - 25 %
Highly reflecting surface	<i>e.g. ice, snow</i>	25 - 35 %

megaso

innovation in power



Electrical data STC

Nominal power (Pmpp)	460 Wp	With bifacial gain ¹	
Nominal voltage (Umpp)	42.0 V	5 %	483 Wp
Nominal current (Impp)	10.96 A	10 %	506 Wp
Open circuit voltage (Uoc)	50.4 V	15 %	529 Wp
Short circuit current (Isc)	11.56 A	20 %	552 Wp
Module efficiency	21.28 %	30 %	598 Wp
Power sorting	-0/+5 %	¹ Depending on mounting distance and albedo of the substrate	

STC (Standard Test Conditions): irradiance 1000 W/m², cell temperature 25°C, AM 1.5
Measuring tolerances ±3 % (Pmpp); ±10 % (Umpp, Impp, Uoc, Isc)

Electrical data at partial load

800 W/m²

Nominal power (Pmpp)	348 Wp
Nominal voltage (Umpp)	39.4 V
Nominal current (Impp)	8.84 A
Open circuit voltage (Uoc)	48.2 V
Short circuit current (Isc)	9.32 A

Measuring tolerances ±3 % (Pmpp); ±10 % (Umpp, Impp)

Thermal properties


Nominal operating cell temperature (NOCT)	45 ± 2 °C
Temperature coefficient Uoc	-0.29 %/°C
Temperature coefficient Isc	+0.049 %/°C
Temperature coefficient Pmpp	-0.39 %/°C

Operating conditions

Temperature range	-40 ... +85 °C
Max. system voltage	1500 V
Max. string fuse	25 A
Max. snow loads *	Up to 7'000 N/m ²
Hail resistance	ø30mm at 23m/s Hail protection class 3
Application class (acc. to IEC/EN61730)	A
Fire protection	Top and back layer are made of heat-resistant glass. The component is considered to be non-combustible material as defined by the Cantonal Fire Insurances.
Protection class	II
Standards	IEC/EN 61215, 61730
Salt spray test	IEC/EN 61701 I+II
Ammonium corrosion test	IEC/EN 62716

* Max. possible forces acting on the module. The maximum values in mounted condition depend on the substructure as well as the installation situation. If the requirements are higher than IEC/EN 61215, a project-specific dimensioning of the mounting system is necessary.

Technical drawing




Note: The instructions in the installation manual must be strictly complied with. Further information about approved utilization of products can be found in the installation manual or can be requested from the technical service.

General data

Laminate structure	Glass-glass
Cell technology	Megasol Mono HiR Bifacial
Cell format	M6 Half-cut 166x83 mm
Number of cells (matrix)	144 (6x 24)
Colour between cells	White
Frame	U-frame 40 mm Aluminium, anodized natural (optional: U30b)
Front side	2.0 mm TVG High-transmission, nano-finished/antireflective surface
Encapsulation material	Special EVA (UV+/IR+) with lowest water vapour permeability
Back side	2.0 mm TVG
Junction box	Split Box, IP67
Cable cross section	4 mm ²
Connectors	MC4-Evo2, IP67
Dimensions (LxWxH) ±3.0 mm	2111 x 1046 x 40 mm
Modular dimensions (LxW)	Depending on the installation situation
Weight	28.5 kg

Quality and warranty

Quality characteristics	PID-free (no potential induced degradation) Yield-optimized low-light performance Full traceability of all raw materials HiR cell technology with enhanced bifaciality factor: additional yields when mounted on flat roof, railing, carport, etc. (depending on mounting distance and albedo of the substrate)
Product warranty	15 years
Linear performance warranty	30 years



Relative efficiency level in relation to the minimal output (%). At least 97% of the minimum output during the first year. Afterwards, max. 0.5% degradation per annum. At least 92.5% of the minimum output after 10 years. At least 87.5% of the minimum output after 20 years. At least 82.5% of the minimum output after 30 years. All data within the measuring tolerances. Warranties according to the respective latest Megasol Warranty Conditions which can be found on www.megasol.ch/warranty.



E-mail: info@megasol.ch
Hotline: +41 62 919 90 90
www.megasol.ch



Megasol partner

Subject to errors and technical modifications. Data sheet in accordance with DIN EN 50380. © Megasol Energy Ltd | Version: 02/2021